CONTENTS.

		PAGE
I.	WOOL FIBRE	. 7
	Cultivation and Mode of Growth—Physical Structure—Difference between Wool, Hair, and Fur—Physical Properties (Strength, Elasticity, Curliness, Lustre, etc.)—How to Retain these during Manufacturing Processes—Felting Property—Avidity for Moisture — Various Methods of Drying Wool—Chemical Composition of Wool—Raw and Purified Wool—Lanuginic Acid—Action on the Fibre of the various Reagents used in the Manufacturing Processes—The 'Carbonising' or 'Extracting' Process.	
II.	Wool Scouring	34
	Object of Wool Scouring—Composition of Wool Yolk—Cholesterol—Manufacture of 'Lanolin'—The Wool-steeping Process—Extraction of Potash Salts from Yolk-ash—Theory of Scouring—The 'Emulsion' and 'Solution' Processes—Composition and Analysis of Scouring Agents—Machinery employed for the Scouring of Loose Wool, Yarn, and Cloth—Recovery of Grease from Waste Scouring Liquors.	
III.	Wool Bleaching	63
	The Tinting Process — The Sulphur Bleach — 'Stoving' or 'Gas Bleaching'—'Liquid' or 'Wet Bleaching'—Hydrosulphite of Soda as a Bleaching Agent—The Peroxide Bleach—Use of Hydrogen, Sodium, and Barium Peroxides—Estimation of Peroxide—Use of Permanganate of Potash.	
IV.	WATER	79
	Sources of Water—Characteristics of Rain, River, Spring, and Well Water—Mechanical and Dissolved Impurities—Lime and Magnesium Salts—Temporary and Permanent 'Hardness'—Iron as an Impurity—Detection and Estimation of Impurities—Effect of Water Impurities during Scouring, Mordanting, and Dyeing Processes—The Technical Purification of Water—Water Purifying Apparetus	

WOOL DYEING.

I.—THE WOOL FIBRE.

IT is a matter of common experience that the quality of the fibre, as indicated by its lustre, strength, and feel (handle), is frequently much poorer in the finished article than in the original raw material, and it is of the utmost importance to enquire whether this cannot be avoided, at any rate partially, by greater skill and care throughout the different manufacturing processes. But in order to comprehend and thoroughly appreciate the effect which the various stages of manufacture—e.g., scouring, dyeing, finishing, etc., will exert upon the wool fibre, it is essential to have a very clear idea of its physical and chemical composition and properties.

What is wool? From the physical point of view it is a peculiar development of the skin of certain animals, and is closely allied to hair and fur. All these are indeed modifications of the same structure, the differences being entirely of degree, and not of kind. In the original wild condition most animals have in fact two skin coverings, the outer one composed of long, straight, stiff hairs, at the roots of which grow much finer, softer, and more numerous fibres, forming the wool or fur. A little confusion arises from the use of the term fur to signify the long hair attached to the skin used for clothing or decorative purposes, in addition to its employment in the more correct sense indicated above. Sealskin is a true fur, the coarse hairs with which the animal is also covered being removed from the skin during the dressing.

By a long course of cultivation and selective breeding, the outer hairy covering with which sheep were originally provided,